

Technical Data Sheet

Polystone[®] FM black

Typical characteristics

- Good sliding properties
- Good mechanical properties

Typical industries

- Building industry

| | Test method | Unit | Guideline value |
|--|-------------------|---------------------|-----------------|
| General properties | | | |
| Density | DIN EN ISO 1183-1 | g / cm ³ | >0,94 |
| Water absorption | DIN EN ISO 62 | % | <0,01 |
| Flammability (Thickness 3 mm / 6 mm) | UL 94 | | HB |
| Mechanical properties | | | |
| Yield stress | DIN EN ISO 527 | MPa | >19 |
| Tensile modulus of elasticity | DIN EN ISO 527 | MPa | >700 |
| Shore hardness | DIN EN ISO 868 | scale D | >63 |
| Compressive strength | ISO 3597-3 | N/mm ² | 4 - 6 |
| Thermal properties | | | |
| Melting temperature | ISO 11357-3 | °C | 130 ... 135 |
| Thermal conductivity | DIN 52612-1 | W / (m * K) | 0,41 |
| Thermal capacity | DIN 52612 | kJ / (kg * K) | 1,90 |
| Service temperature, long term | Average | °C | -80 ... 80 |
| Service temperature, short term (max.) | Average | °C | 100 |

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
 info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 10/10/2024 • Release: 20/09/2023 • Version: 1.0
 PIM-Version: 572 • PIM-ID: 591163 • PIM-Code: 572-26-223.17-8-5

